

**ELECTRONIC FILTER INCLUDING
LANGASITE STRUCTURE COMPOUND
AND METHOD FOR MAKING SAME**

Related Application

The present application is based upon
copending provisional application serial no. 60/201,435
filed on May 3, 2000, the entire contents of which are
5 incorporated herein by reference.

Field of the Invention

This invention relates to electronic filters,
and more particularly to filters including a Langasite
structure compound and associated methods.

10

Background of the Invention

Bulk acoustic wave (BAW) and surface acoustic
wave (SAW) devices are two key components in today's
wireless electronic systems. These devices serve the
two major functions of signal processing and frequency
15 control. The signal processing function involves
filtering of electrical signals which typically have a
frequency ranging from several MHZ up to several GHz
and a fractional passband from as low as less than a
few hundredths of a per-cent up to tens of a per-cent.

20

The frequency control function involves
generating a precise clock signal or a frequency source
whose frequency ranges between several MHZ up to

several hundred MHZ. Passive BAW and SAW filters as well as BAW and SAW resonator based clocks and oscillators have been, and will continue to be, the mainstay for these signal processing and frequency control applications.

BAW and SAW filters and resonators are electromechanical devices operated based upon the piezoelectric effect. The piezoelectric materials used for BAW and SAW devices are predominantly of single crystal form. Fundamentally the performance of acoustic wave devices depends on the piezoelectric crystal's electromechanical coupling strength, its inherent acoustic loss, and its temperature stability.

Another material property of interest for BAW and SAW device construction is the acoustic velocity. The merit of acoustic velocity depends on desired application. For example, higher velocity crystals allow fabrication of devices with higher operating frequencies. On the other hand, for certain SAW filter constructions, namely the ones involving classical transversal filters, a higher velocity crystal substrate may suffer from a larger required device size.

The electromechanical coupling strength dictates the efficiency of energy conversion from electrical to acoustic energy and vice versa, and is thus important to the device insertion loss. The inherent acoustic loss also affects the device insertion loss. Perhaps more importantly the inherent acoustic loss manifests itself into affecting the fidelity of the BAW and SAW resonators in the form of the resonance quality factor Q . This has a direct bearing on the frequency stability of the oscillator constructed using the resonator. A "material Q factor" has long been recognized in the field of crystal (BAW)

resonators and oscillators, and later adapted by workers in the SAW resonator field.

The maximum material Q , established empirically, is inversely proportional to the device frequency. For a given piezoelectric material, this corresponds to a constant $Q_{\max} \cdot f$ factor. For example, for the commonly used BAW and SAW crystal cuts:

$$(Q_{\max} \cdot f)_{\text{BAW}} = 1.6 \times 10^{13} \text{ Hz for AT and SC cuts}$$

$$(Q_{\max} \cdot f)_{\text{SAW}} = 1.1 \times 10^{13} \text{ Hz for ST cut}$$

The temperature stability of the piezoelectric crystal dictates how stable, typically in terms of device frequency in parts per million, an acoustic device performs with changing ambient temperature.

The compound Langasite ($\text{La}_3\text{Ga}_5\text{SiO}_{14}$, LGS) was first reported in Russia back in 1980 with a $\text{Ca}_3\text{Ga}_2\text{Ge}_4\text{O}_{14}$ type structure. It was found then to have attractive laser, electromechanical and acoustic properties. Interest in LGS has grown in recent years for acoustic device applications. LGS has the same point group (32) symmetry as quartz. Similar to quartz, it has temperature compensated crystal orientations suitable for building temperature-stable BAW and SAW devices.

In comparison with quartz it has the advantage of higher electromechanical coupling strength. With a slower acoustic velocity, it has the potential for miniaturized wideband SAW filters suitable for hand-held mobile wireless devices, for example. LGS was also cited for its potential of lower acoustic loss due to the heavier atomic species of La and Ga, although LGS actually has higher acoustic loss than quartz due to its disordered structure.

Langasite is not unique with these attractive properties. It is just one crystal belonging to a very large family of crystals which have the same structure,

and which are called the Langasite family compounds. In fact, compounds within this family typically have quite similar properties. In other words, they are non-centro-symmetric and thus piezoelectric. But they do have some variation due to the difference in composition of each compound. The constants that can be affected by composition include the lattice constant, thermal expansion coefficient, acoustic velocity, dielectric constant, and electromechanical coupling constant, as well as the temperature coefficients of all these constants. These variations, in general, are small (within a factor of 2 or less) but still can have a very significant effect on the device performance.

The Langasite structure is very complex for anhydrous compounds. It has four distinct cation sites. They include three dodecahedral (Site A), one octahedral (Site B), three large tetrahedral (Site C) and two small tetrahedral (Site D) sites. Each site can only accommodate a certain size and charge of the cations. Even with this constraint, nearly one hundred combinations of the cation composition are possible within the structure. Each combination must satisfy the charge neutrality requirement. In almost all the cases, it is necessary to fit a specific site with more than one type of element with different ionic charges in order to satisfy the charge neutrality. This kind of charge balance process creates disorder for the particular site and thus the whole crystal.

For example, LGS has three La ions in the dodecahedral site, one Ga ion in the octahedral site, three Ga ions in the large tetrahedral site and finally one Ga ion and one Si ion in the small tetrahedral sites. The locations of both Ga and Si ions are totally random (or "disordered") within the smaller

tetrahedral site. Since Ga is 3+ charged and Si is 4+ charged, there is a disorder of ionic charge. In addition, since Ga and Si have a difference in ionic size, mass and density, this creates additional
5 disorder in the lattice of the crystal.

Another example is Langanite ($\text{La}_3\text{Nb}_{0.5}\text{Ga}_{5.5}\text{O}_{14}$, LGN) where the disorder is located at the single octahedral sites. In this case, half of the octahedral sites are occupied by Nb ions, and the other half occupied by Ga ions.

10 Thus the charge difference is even higher than LGS with Nb 5+ charged and Ga 3+ charged.

A third example is CGG ($\text{Ca}_3\text{Ga}_2\text{Ge}_4\text{O}_{14}$). Here the disorder is located at the large tetrahedral site where 2/3 of the sites are occupied by Ge with a 4+ charge and 1/3
15 of the sites are occupied by Ga with a 3+ charge.

A fourth example is NSGG ($\text{NaSr}_2\text{GaGe}_5\text{O}_{14}$). Here the disorder is located at the dodecahedral site where 2/3 of the sites are occupied by Sr with a 2+ charge and 1/3 of the sites are occupied by Na with a 1+
20 charge.

A fifth example is LSFG ($\text{LaSr}_2\text{Fe}_3\text{Ge}_3\text{O}_{14}$). Here the disorder occurs in two different sites. The first one is the dodecahedral site where 1/3 of the sites are occupied by La with a 3+ charge and 2/3 of the sites
25 are occupied by Sr with a 2+ charge. The second one is the large tetrahedral site where 2/3 of the sites are occupied by Fe with a 3+ charge and 1/3 of the sites are occupied by Ge with a 4+ charge.

Structure disorder may not be a desirable
30 feature for crystals to be used in certain acoustic and optical applications. The classic example is glass. Glass is totally disordered from a structural point of view. Even though it has good optical transmission, it is not a good laser host because the local disorder of

14-00000-243869

The problem of disorder for acoustic
ons is the typically high acoustic loss.

It should be noted that, despite the disordered structure, high quality single crystal Y-cut Lngasite isomorphs LGN and LGT ($\text{La}_3\text{Ta}_{0.5}\text{Ga}_{5.5}\text{O}_{14}$) have already been demonstrated to show higher material Q than quartz, with $Q_{\text{max}} \cdot f$ product reaching as high as $(Q_{\text{max}} \cdot f)_{\text{LGN BAW}} = 2.2 \times 10^{13} \text{ Hz}$ and $(Q_{\text{max}} \cdot f)_{\text{LGT BAW}} = 2.9 \times 10^{13} \text{ Hz}$.

Applicants have tried to grow a single crystal of LTG, but found that it is not possible to grow it directly from the melt, because of the reduction of Ti^{4+} to Ti^{3+} under the growth conditions where the iridium crucible is stable. As a

consequence, there were not sufficient 4+ charge ions in the melt to produce LTG.

Even though charge neutrality may be the most important factor controlling the composition of

5 Langasite structure compounds, it is not the only factor. The ionic size and also the thermal stability should also be considered to make the composition compatible. The choice of cations to fit into any specific site is a very difficult task with no

10 guarantee that the selected combination will work. The reason is that there is not sufficient data to predict its thermodynamic properties. Unless the selected composition has the lowest free energy, the compound will not exist. The only way to prove its existence is

15 to actually synthesize the compound according to the proposed composition. When the composition is properly selected, it is possible to fit each cation into a specific site with a total balance of electric charge.

20 An article by B.V. Mill, et al., "Synthesis, Growth and Some Properties of Single Crystals with the $\text{Ca}_3\text{Ga}_2\text{Ge}_4\text{O}_{14}$ Structure", Proc. 1999 Joint Meeting EFTF - IEEE IFCS, pp.829-834 discloses numerous synthesized Langasite family compositions, among which are the

25 group of $\text{A}^{2+}_3\text{X}^{5+}\text{Y}^{3+}_3\text{Z}^{4+}_2\text{O}_{14}$, with A=Ca, Sr, Ba, Pb; X=Sb, Nb, Ta; Y=Ga, Al, Fe, In; Z=Si, Ge. The article identifies nine individual compounds that are grown according to the Czochralski technique, and of these only three were further identified as having a good

30 chance to become piezoelectric materials for digital mobile communications systems and other acoustic applications in the 21st century. These three materials are $\text{La}_3\text{Ga}_5\text{SiO}_{14}$, $\text{La}_3\text{Nb}_{0.5}\text{Ga}_{5.5}\text{O}_{14}$ and $\text{La}_3\text{Ta}_{0.5}\text{Ga}_{5.5}\text{O}_{14}$.

An article by H. Takeda, et al., "Synthesis

35 and Characterization of $\text{Sr}_3\text{TaGa}_3\text{Si}_2\text{O}_{14}$ Single Crystals",

100-101-102-103-104-105-106-107-108-109-110-111-112-113-114-115-116-117-118-119-120-121-122-123-124-125-126-127-128-129-130-131-132-133-134-135-136-137-138-139-140-141-142-143-144-145-146-147-148-149-150-151-152-153-154-155-156-157-158-159-160-161-162-163-164-165-166-167-168-169-170-171-172-173-174-175-176-177-178-179-180-181-182-183-184-185-186-187-188-189-190-191-192-193-194-195-196-197-198-199-200-201-202-203-204-205-206-207-208-209-210-211-212-213-214-215-216-217-218-219-220-221-222-223-224-225-226-227-228-229-230-231-232-233-234-235-236-237-238-239-240-241-242-243-244-245-246-247-248-249-250-251-252-253-254-255-256-257-258-259-260-261-262-263-264-265-266-267-268-269-270-271-272-273-274-275-276-277-278-279-280-281-282-283-284-285-286-287-288-289-290-291-292-293-294-295-296-297-298-299-300-301-302-303-304-305-306-307-308-309-310-311-312-313-314-315-316-317-318-319-320-321-322-323-324-325-326-327-328-329-330-331-332-333-334-335-336-337-338-339-340-341-342-343-344-345-346-347-348-349-350-351-352-353-354-355-356-357-358-359-360-361-362-363-364-365-366-367-368-369-370-371-372-373-374-375-376-377-378-379-380-381-382-383-384-385-386-387-388-389-390-391-392-393-394-395-396-397-398-399-400-401-402-403-404-405-406-407-408-409-410-411-412-413-414-415-416-417-418-419-420-421-422-423-424-425-426-427-428-429-430-431-432-433-434-435-436-437-438-439-440-441-442-443-444-445-446-447-448-449-450-451-452-453-454-455-456-457-458-459-460-461-462-463-464-465-466-467-468-469-470-471-472-473-474-475-476-477-478-479-480-481-482-483-484-485-486-487-488-489-490-491-492-493-494-495-496-497-498-499-500-501-502-503-504-505-506-507-508-509-510-511-512-513-514-515-516-517-518-519-520-521-522-523-524-525-526-527-528-529-530-531-532-533-534-535-536-537-538-539-540-541-542-543-544-545-546-547-548-549-550-551-552-553-554-555-556-557-558-559-560-561-562-563-564-565-566-567-568-569-570-571-572-573-574-575-576-577-578-579-580-581-582-583-584-585-586-587-588-589-590-591-592-593-594-595-596-597-598-599-600-601-602-603-604-605-606-607-608-609-610-611-612-613-614-615-616-617-618-619-620-621-622-623-624-625-626-627-628-629-630-631-632-633-634-635-636-637-638-639-640-641-642-643-644-645-646-647-648-649-650-651-652-653-654-655-656-657-658-659-660-661-662-663-664-665-666-667-668-669-670-671-672-673-674-675-676-677-678-679-680-681-682-683-684-685-686-687-688-689-690-691-692-693-694-695-696-697-698-699-700-701-702-703-704-705-706-707-708-709-710-711-712-713-714-715-716-717-718-719-720-721-722-723-724-725-726-727-728-729-730-731-732-733-734-735-736-737-738-739-740-741-742-743-744-745-746-747-748-749-750-751-752-753-754-755-756-757-758-759-760-761-762-763-764-765-766-767-768-769-770-771-772-773-774-775-776-777-778-779-780-781-782-783-784-785-786-787-788-789-790-791-792-793-794-795-796-797-798-799-800-801-802-803-804-805-806-807-808-809-810-811-812-813-814-815-816-817-818-819-820-821-822-823-824-825-826-827-828-829-830-831-832-833-834-835-836-837-838-839-840-841-842-843-844-845-846-847-848-849-850-851-852-853-854-855-856-857-858-859-860-861-862-863-864-865-866-867-868-869-870-871-872-873-874-875-876-877-878-879-880-881-882-883-884-885-886-887-888-889-890-891-892-893-894-895-896-897-898-899-900-901-902-903-904-905-906-907-908-909-910-911-912-913-914-915-916-917-918-919-920-921-922-923-924-925-926-927-928-929-930-931-932-933-934-935-936-937-938-939-940-941-942-943-944-945-946-947-948-949-950-951-952-953-954-955-956-957-958-959-960-961-962-963-964-965-966-967-968-969-970-971-972-973-974-975-976-977-978-979-980-981-982-983-984-985-986-987-988-989-990-991-992-993-994-995-996-997-998-999-1000

Material Research Bulletin, vol. 35 (2000), pp. 245-252, cited previous work of polycrystal STGS by Mill, et al., (Russ. Jour. Inorg. Chem., vol. 43, p.1168 (1998), and disclosed the synthesis and
5 characterization of $\text{Sr}_3\text{TaGa}_3\text{Si}_2\text{O}_{14}$ (STGS). The article further disclosed that STGS resonators were prepared and the piezoelectric properties thereof were determined.

Despite continuing development in the area of
10 Langasite structure compounds for electronic devices, there still exists a need for further development work to identify and produce such compounds with desirable properties and that can be used to produce high frequency electronic filters.

15 Summary of the Invention

In view of the foregoing background, it is therefore an object of the present invention to provide an electronic filter that includes a piezoelectric layer based on a Langasite structure that is readily
20 manufacturable and/or which enjoys advantageous operating characteristics.

This and other objects, features and advantages in accordance with the present invention are provided by an electronic filter comprising a
25 piezoelectric layer including an ordered Langasite structure compound having the formula $\text{A}_3\text{BC}_3\text{D}_2\text{E}_{14}$, wherein A is strontium, B is tantalum, C is gallium, D is silicon, and E is oxygen; and a plurality of pairs of electrodes connected to the piezoelectric layer to
30 perform a filtering function in cooperation with the piezoelectric layer. The ordered Langasite structure compound may have a substantially perfectly ordered structure.

In comparison with the established material of choice to-date, quartz, the ordered Langasite structure compound of the present invention enjoys a lower acoustic loss and higher material Q due, possibly due to the perfect ordering and heavy elements. The ordered Langasite structure compound may also enjoy a higher electromechanical coupling factor possibly due to stronger piezoelectric effect resulting from the crystal structure and Ta in the octahedral sites.

These factors may be important for high performance bulk and surface acoustic wave filtering devices, for example. Furthermore, the crystal symmetry of point group 32 may provide temperature compensated orientations with which devices can be manufactured for minimal temperature variation induced frequency and group delay shifts.

Each of the plurality of pairs of electrodes may include first and second interdigitated electrodes. Moreover, the plurality of pairs of electrodes may be connected to a same face of the piezoelectric layer so that the electronic filter is a surface acoustic wave (SAW) filter. In other embodiments, the plurality of pairs of electrodes may comprise first and second pairs of electrodes connected to respective opposing first and second faces of the piezoelectric layer so that the electronic filter is a bulk acoustic wave (BAW) filter.

The ordered Langasite structure compound may be readily producible using a melt pulling crystal growth technique, especially since the components have congruent melting properties. In addition, the ordered Langasite structure compound may have a relatively high thermally stability.

A method aspect of the invention is for making an electronic filter. The method may comprise providing a piezoelectric layer comprising an ordered

Langasite structure compound having the formula $A_3BC_3D_2E_{14}$, wherein A is strontium, B is tantalum, C is gallium, D is silicon, and E is oxygen; and connecting a plurality of pairs of electrodes to the piezoelectric layer to cooperate therewith and perform a filtering function. The ordered Langasite structure compound may have a substantially perfectly ordered structure.

Brief Description of the Drawings

FIG. 1 is a perspective schematic view of a SAW filter device in accordance with the present invention.

FIG. 2 is a perspective schematic view of a BAW filter in accordance with the present invention.

Detailed Description of the Preferred Embodiments

The present invention will now be described more fully hereinafter with reference to the accompanying drawings, in which preferred embodiments of the invention are shown. This invention may, however, be embodied in many different forms and should not be construed as limited to the embodiments set forth herein. Rather, these embodiments are provided so that this disclosure will be thorough and complete, and will fully convey the scope of the invention to those skilled in the art. Like numbers refer to like elements throughout.

The present invention is directed to an electronic filter, such as for signal filtering, for example. The filter preferably comprise a piezoelectric layer including an ordered Langasite structure compound having the formula $A_3BC_3D_2E_{14}$, wherein A is strontium, B is tantalum, C is gallium, D is silicon, and E is oxygen. Each filter also preferably includes a plurality of pairs of electrodes configured

Briefly, in comparison with the established material of choice to-date, quartz, the ordered Langasite structure compound of the present invention enjoys a lower acoustic loss and higher material Q due, possibly due to the perfect ordering and heavy elements. The ordered Langasite structure compound may also enjoy a higher electromechanical coupling factor possibly due to stronger piezoelectric effect resulting from the crystal structure and Ta in the octahedral sites. These factors may be important for high performance bulk and surface acoustic wave devices, for example. Furthermore, the crystal symmetry of point group 32 may provide temperature compensated orientations with which devices can be manufactured for minimal temperature variation induced frequency and group delay shifts.

The SAW filter **20** as shown in FIG. 1 includes a piezoelectric layer **21** formed of STGS as described herein. A first pair of interdigitated electrodes **22a**, **23a** are illustratively formed on or connected to the upper face of the layer **21**. A second pair of interdigitated electrodes **22b**, **23b** are also formed on or connected to the upper face in spaced relation from the first pair. In the illustrated embodiment, optional passive end electrodes **24**, **25** are also provided. Those of skill in the art will also appreciate other equivalent configurations of electrodes that will produce a SAW filter as contemplated by the present invention. Those of skill in the art will appreciate that the SAW filter **20** can

be used in any of a number of high frequency filtering circuits, such as particularly for those used in portable wireless communications devices, such as cellular telephones.

5 Turning now to FIG. 4, the illustrated BAW filter **40** also includes a piezoelectric layer **41** formed of STGS as described herein. In the illustrated embodiment, a first pair of interdigitated electrodes **42a, 43a** are formed on a first or upper surface of the
10 piezoelectric layer **41**, and second pair of interdigitated electrodes **42b, 43b** are formed or connected to the second or lower face of the piezoelectric layer. Other configurations of electrodes are also contemplated by the invention as
15 will be appreciated by those skilled in the art. Those of skill in the art will also appreciate the many varied electronic circuit applications for the BAW filter **40** without further discussion herein.

 Having now described exemplary electronic
20 filters **20, 40** that may use the STGS piezoelectric materials of the present invention, those of skill in the art will appreciate other similar electronic filters. Accordingly, Applicants now further describe additional features and characteristics of the ordered
25 Langasite structure compound, STGS.

 The Langasite structure compound has four distinct cation sites. However, it is interesting to know that only the cation size of the large tetrahedral site may be the most critical one to determine the
30 stability of this structure. This site requires ions with the radius around 0.6 Å. The only ions that have such size and can satisfy the electric charge requirement are Ga^{3+} and Ge^{4+} .

2025 RELEASE UNDER E.O. 14176

In fact, a majority of the Langasite structure compounds contain germanium. However, in accordance with this invention, the Ge-containing Langasite structures are eliminated from consideration.

5 The reason is not because of the order-disorder structure, but rather because of the thermal stability. GeO_2 has too low a thermal stability and evaporates profusely under melting condition. It is not possible to grow large, high quality single crystals of Ge-
10 containing Langasite using the current known melt pulling techniques. Therefore, Applicants have concentrated only on the ordered Ga-containing Langasite structure compounds.

Since it is not possible to make ordered-
15 structure La-containing Langasite compounds, Applicants switch to the alkali-earth containing Langasite structure compounds. Two possible compositions that are possible to fulfill both the charge neutrality and site selection requirements and still retain an ordered
20 structure is STGS -- $\text{Sr}_3\text{TaGa}_3\text{Si}_2\text{O}_{14}$. One should notice that the germanium equivalent compounds also satisfy the same requirement. However, Si is selected over Ge because SiO_2 has much higher temperature stability and does not evaporate at the melting temperature of these
25 compositions.

Since the Si^{4+} ion is much smaller than the Ge^{4+} ion, it reduces the lattice constants quite significantly. It was found possible to produce high quality single crystals of STGS. Applicants also
30 theorize that BNGG ($\text{Ba}_3\text{NbGa}_3\text{Ge}_2\text{O}_{14}$) and BTGG ($\text{Ba}_3\text{TaGa}_3\text{Ge}_2\text{O}_{14}$) compounds can be synthesized since other Ba-containing Langasite structure compounds do exist such as BGG ($\text{Ba}_3\text{Ga}_2\text{Ge}_4\text{O}_{14}$), although conventional melt flow pulling techniques may not be sufficient.

FILED IN 346460

The demonstration of the existence of a particular composition is just the first step towards the production of a crystal. It shows that this composition is indeed thermodynamically stable. To be
5 able to grow a crystal directly from melt, it is needed to demonstrate that this composition is stable all the way to melting without any solid state phase transition nor thermal dissociation.

At the same time, a melt with this property
10 will crystallize a crystal with the same composition as the melt. This property is called congruent melting. Congruent melting may be highly desirable for practical crystal production, but a much harder property to realize. In fact, the majority of the known compounds
15 do not melt congruently. The likelihood to be congruently melting decreases dramatically as the number of components in the melt increases.

For example, essentially all single element melts are congruent, such as Si, or Ge, etc. Examples
20 of two element congruent melts include Al_2O_3 , GaAs, etc. Both SiO_2 , ZnS are not congruent melting. Examples of three element congruent melts include YAG ($\text{Y}_3\text{Al}_5\text{O}_{12}$), LiNbO_3 , etc. The known numbers of four element congruent melts are even fewer. It turns out that
25 Langasite family compounds have many congruent melting compositions such as LGS, LGN and LGT. Other known four-element congruent melts include GSGG ($\text{Gd}_3\text{Sc}_2\text{Ga}_3\text{O}_{12}$), SFAP ($\text{Sr}_5\text{P}_3\text{O}_{12}\text{F}$), YCOB ($\text{YCa}_4\text{B}_3\text{O}_{10}$).

One of the interesting things observed with
30 STGS is the congruent melting nature of this compounds. In fact, Applicants believe that it is among the first known composition systems that contain truly four oxide components (or five elements total) and melt congruently. In other words, each element is located

in a specific site without mixing or solid solution among themselves.

For example a Nd doped LGT crystal contains four oxide components, namely, Nd_2O_3 , La_2O_3 , Ta_2O_5 and 5 Ga_2O_3 . But it is not a true four component system, since Nd and La occupy the same dodecahedral site and thus structurally they are indistinguishable. Therefore, Nd-LGT is still a three oxide component (or 10 four element) system.

For the compound disclosed here, we found that once the melt composition is properly adjusted, we can practically use the entire melt to grow the crystals. This is significant since this means that there is very little selective evaporation of the 15 components and these crystals are suitable for mass production with very little material waste. This reduces the crystal manufacturing cost.

In addition, among all the oxide components used in the Langasite family compound growth, the most 20 expensive one is GeO_2 followed by Ga_2O_3 . As mentioned earlier, in accordance with the invention, Ge-containing compounds are avoided not just because of their cost, but more so because of their instability due to volatilization of GeO_2 .

For LGS, LGN and LGT, the use of Ga_2O_3 is 25 quite expensive, a 5, 5.5 and 5.5 factor per formula, respectively. This has been a concern for the eventual commercialization of these compounds because of their high chemical cost as compared with quartz (SiO_2) or 30 LiNbO_3 . The industry may be so accustomed to the low cost of quartz and LiNbO_3 wafers, it may likely be quite reluctant to accept the high cost of Langasite wafers despite their better properties. In the case of the new compound, the Ga_2O_3 usage is reduced by almost half. 35 It will certainly help to reduce the wafer cost.

5 therefore more suited than quartz for manufacture of
bulk acoustic wave filters of wider passband and lower
insertion loss. The symmetry of the crystal structure
may lead to a range of temperature compensated crystal
orientations so that bulk acoustic wave devices
0 manufactured with this ordered Langasite structure
compound incur minimal shifts in frequency and group
delay induced by ambient temperature variation.

20 The crystal was grown by the traditional
Czochralski pulling technique in a nitrogen atmosphere.
The seed orientation is in (010) direction. During the
initial melting of the charge, it is noticed that the
viscosity of the crystal is much higher than the
25 traditional Langasite composition. This creates an
additional difficulty for crystal growth. One of the
typical defects is the core defect. A higher rotation
rate may be needed to eliminate the opaque core region.
The rotation rate is from 15 to 22 rpm and the pulling
30 rate is from 1 to 1.5 mm/hr.

Since higher rotation rate also introduces melt flow instability, the rotation is reduced as soon as the crystal reaches its intended diameter. At present, the domain structure is overcome by reducing the growth cone angle. The crystal obtained was

examined by X-ray diffraction, yielding the lattice parameters $a=8.299 \text{ \AA}$ and $c=5.079 \text{ \AA}$. The STGS crystal in accordance with the present invention provided the following comparative characteristics:

5	MATERIAL	$K^2(\%)$	SAW VELOCITY	ϵ_{11}	ϵ_{33}
	ST Quartz	0.134	3156	4.53	4.68
	LGS	0.3 ~ 0.38	2350	19.62	49.41
	LGN	0.43	2300	20.089	79.335
10	LGT	0.38	2220	18.271	78.95
	STGS	0.559	2740	13.15	17.97

It is further theorized that the containing of heavy elements in the compound reduces the phonon energy of the crystals. It is further theorized that the perfect structural ordering further reduces the incoherent phonon scattering. Combinations of these two properties make the ordered Langasite compounds STGS produce a higher Q material as compared to other piezoelectric materials. These materials are advantageously used in accordance with the electronic filter and associated methods described above. Other similar devices and methods are disclosed in copending patent applications entitled, "ELECTRONIC DEVICE INCLUDING LANGASITE STRUCTURE COMPOUNDS AND METHOD FOR MAKING SAME", having attorney work docket no. 59625, and "ELECTRONIC DEVICE INCLUDING LANGASITE STRUCTURE COMPOUND AND METHOD FOR MAKING SUCH DEVICES", having attorney work docket no. 59685, both filed concurrently herewith, and the entire disclosures of which are incorporated herein by reference.

5